

# ST-316L

Low carbon 18%Cr-12%Ni-2%Mo STS

CE

## Conformances

AWS A5.9/ ASME SFA5.9 ER316L  
 JIS Z3321 YS316L  
 EN ISO 14343-A W 19 12 3L  
 KR RY316L (-196°C ≥29 J)  
 ABS AWS A5.9 ER316L  
 LR 316L (-196°C)  
 BV 316L (KV -196°C)  
 DNV-GL VL 316L (-196°C)  
 NK KY316L  
 CCS 316L  
 CWB AWS A5.9 ER316L  
 CE

## Current

DC -

## Shielding Gas

Ar

## Diameter / Packaging

Diameter	
mm (in)	5kg*1000
1.0 (0.039)	✓
1.2 (0.045)	✓
1.6 (1/16)	✓
2.0 (5/64)	✓
2.4 (3/32)	✓
2.6 (0.10)	✓
3.2 (1/8)	✓

## Applications

- Steel Structures - Chemical industries and nuclear reactors

## Features

- Excellent crack resistance
- Excellent resistance to heat
- Excellent Arc stability and bead wetting

## Typical Chemical Composition of the Wire(%)

C	Si	Mn	Cr	Ni	Mo
0.02	0.38	1.85	18.8	12.4	2.5

## Typical Mechanical Properties of All-Weld Metal

TS MPa(lbs/in <sup>2</sup> )	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft·lbs)
570 (82,700)	44	0 (32)	140 (103)

SMAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX