

S-7016.HR

COVERED ARC WELDING ELECTRODE
FOR 490MPa CLASS HIGH TENSILE STEEL



❖ Specification

AWS A5.1	E7016 H4R
JIS Z3211	E4916
EN ISO 2560-A	E42 3 B 1 2 H5

❖ Applications

Structures using 490MPa class high tensile steel, bridges, buildings, ship, high pressure vessels, rolling stock and off-shore structures.

❖ Characteristics on Usage

S-7016.HR is the extra low-hydrogen (HDM < 4ml/100g) electrode for all positions welding of 490MPa class high tensile steel. X-ray performance and mechanical properties of weld metal are excellent. The usability such as arc smoothness, slag detachability and bead appearance are good and easy to weld in all position.

❖ Note on Usage

1. Dry the electrodes at 300~350°C (572~662°F) for 30~60 minutes before use.
2. Keep the arc as short as possible, and avoid large width weaving.
3. Adopt back step method or strike the arc on a small steel plate prepared for this particular purpose to prevent blowholes at the arc starting.
4. Use the wind screen against strong wind.




Mechanical Properties & Chemical Compositions of All Weld Metal

❖ Welding Conditions

Measurement method	: AWS A5.1
Diameter	: 4.0 X 400(5/32 X 16)
Welding position	: Flat (1G-PA)
Welding Polarity	: AC
Pass & Layers	: 15Passes – 7Layer
Interpass Temp. °C(°F)	: 105~175 (221~347)
Test plate	: ASTM A36 (groove shape as below)

❖ Groove configuration



[Joint Preparation & Layer Details]

Notes:

- Groove angle : 20°+5°
- plate thickness : 20mmt
- Root opening : 16mm
- Test plate width : 150mm (min. 125)
- Test plate Length : 300mm (min. 250)

[Welding parameters]

size (mm)	Welding position	Polarity	Pass	condition		Speed (cm/min)	Heat-Input (kJ/cm)	Interpass temperature (°C)
				Current (A)	Voltage (V)			
4.0* 400	1G (PA)	AC	1	160	24	15.5	14.2	27
			2	160	24	15.2	15.2	47
			3	170	25	16.4	15.5	110
			4	170	25	16.8	15.2	112
			5	170	25	16.0	15.9	110
			6	170	25	16.3	15.6	107
			7	170	25	16.9	15.0	105
			8	170	25	16.3	15.6	110
			9	170	25	16.0	15.9	118
			10	170	25	16.8	15.2	114
			11	170	25	16.2	15.7	111
			12	170	25	15.9	16.0	105
			13	170	25	16.3	15.6	107
			14	170	25	15.5	16.5	110
			15	170	25	15.8	16.1	108

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Mechanical Properties & Chemical Compositions of All Weld Metal

❖ Mechanical Property of All Weld Metal

Size mm(in)	Tensile test			CVN Impact Test J (ft·lbs)
	YS MPa (ksi)	TS MPa (ksi)	EL (%)	-30°C(-22°F)
3.2(1/8)	501(73)	573(83)	29.7	112(83)
4.0(5/32)	493(71)	561(81)	153	153(113)
AWS Spec.	≥ 400(58)	≥ 490(71)	≥ 22	≥ 27(20)

❖ Chemical Composition of All Weld Metal(wt%)

Size mm(in)	Chemical Composition (%)				
	C	Si	Mn	P	S
3.2(1/8)	0.07	0.59	1.00	0.011	0.006
4.0(5/32)	0.07	0.57	0.95	0.012	0.005
AWS Spec.	≤0.15	≤0.75	≤1.60	≤0.035	≤0.035

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Absorbed Moisture contents & Diffusible Hydrogen Content

❖ Absorbed Moisture contents

Measurement method	: AWS A4.4
Diameter	: 3.2mm(1/8in), 4.0mm(5/32in)
Exposed environment	: 30°C(86°F) and 80% Relative humidity (RH)
Exposed Time	: 3~12 hours (* AWS requirement is period of not less than 9 hours)
Analysis method	: Infrared Detector
Limit of moisture content "E7016"	: As-Received or Reconditioned (≤0.6%) / As-Exposed (N.S)
"E7016 H4R"	: As-Received or Reconditioned (≤0.3%) / As-Exposed (≤0.4%)

Size mm(in)	Absorbed moisture contents (wt%)				
	As-received	2hr	4hr	6hr	9hr
3.2(1/8)	0.069	0.076	0.099	0.110	0.130
4.0(5/32)	0.077	0.088	0.112	0.105	0.111

❖ Diffusible Hydrogen Content

Diameter	: 3.2mm(1/8in), 4.0mm(5/32in)
Exposed environment	: 30°C(86°F) and 80% Relative humidity (RH)
Exposed time	: 3~9 hours
Re-drying conditions	: 350°C X 1hr (662°F X 1hr)
Welding current	: 3.2mm(1/8in) = 140Amp, AC 4.0mm(5/32in) = 170Amp, AC
Test method	: AWS A4.3 (Gas chromatography method)

Size mm(in)	Diffusible hydrogen content (ml/100g)				
	X1	X2	X3	X4	Ave.
3.2(1/8)	3.35	2.87	3.49	2.99	3.18
4.0(5/32)	3.27	3.22	2.69	3.18	3.09

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.

**Weldability
& Welding Efficiency Test****❖ Weldability**

Item \ Division	Flat position	Vertical position
Arc stability	Good	Good
Melting rate	Excellent	Excellent
Deposition rate	Excellent	Excellent
Resistance of spatter occurrence	Excellent	Excellent
Bead appearance	Good	Good
The others	Good	Good

❖ Test Conditions of Deposition Efficiency

Consumable	Base Metal		Welding conditions		
	Specification	Dimension, mm(in)	Amp. (A)	Welding speed (mm/min)	Position
S-7016.HR (4.0 x 400 mm) (5/32 x 16 in)	ASTM A36	300 X 100 X12 (12 X 3.9 X 0.5)	170	200	Flat

❖ Results of Deposition Efficiency Test

Consumable	Deposition efficiency(%)	
	For electrode	For core wire
S-7016.HR 4.0 x 400 mm (5/32 x 16 in)	63 ~ 66	96 ~ 100

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.



Size Available and recommended Current

❖ Sizes Available and Recommended Current

Diameter, mm(in)		2.6 (3/32)	3.2 (1/8)	4.0 (5/32)	5.0 (3/16)	6.0 (15/64)
Length, mm(in)		350(14)	350(14)	400(16)	400(16)	450(18)
Recommended current range (AC or DC+ Amp.)	Flat position	55 ~85	90 ~130	130 ~180	180 ~240	250 ~310
	Vertical & Overhead position	50 ~80	80 ~120	110 ~170	150 ~200	-

This information is provided solely for the purpose of confirming product conformance with applicable standards. The serviceability of a product or structure utilizing this type of information is and must be the sole responsibility of the builder/user. Many variables beyond the control of HYUNDAI WELDING CO., LTD. affect the results obtained in applying this type of information. These variables include, but are not limited to, welding procedure, shielding gas, plate chemistry and temperature, weldment design, fabrication methods and service requirements.